

OPzV series is a Valve Regulated Lead Acid battery that adopts immobilized GEL and Tubular Plate technology to offer high reliability and performance. The Battery is designed and manufactured according to DIN standards and with die-casting positive grid and patent formula of active material. OPzV series exceeds DIN standard values with more than 20 years floating design life at 25°C and is even more suitable for cyclic use under extreme operating conditions.


## Specification

Voltage Per Unit	2V(single cell)
Capacity	1200Ah@10hr-rate to 1.80V per cell @25°C
Weight	Approx. 90 Kg
Max. Discharge Current	4000 A (5 sec)
Internal Resistance	Approx. 0.25 mΩ
Operating Temperature Range	Discharge: -40°C~70°C Charge: 0°C~50°C Storage: -20°C~60°C
Optimal Operating Temperature Range	25°C± 5°C
Float charging Voltage	2.25 to 2.3 VDC/unit Average at 25°C
Maximum Charging Current Limit	240 A
Cycle Service	2.37 to 2.40 VDC/unit Average at 25°C
Self Discharge	Self-discharge ratio less than 2% per month at 25°C. Please charge batteries before using.
Terminal	Thread insert & Bolt (F10-M8)
Container Material	A.B.S. (UL94-HB), and UL94-V0 is optional



ISO9001:2000 Certificate

## Dimensions



## Constant Current Discharge Characteristics : A(25°C)


F.V/ Time	30min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.90	590.4	468.0	330.0	250.3	205.2	177.3	159.6	124.5	106.8	56.40
1.87	660.0	516.0	354.0	265.4	216.6	186.5	169.2	130.4	111.6	58.80
1.83	756.0	576.0	384.0	282.9	228.0	194.6	175.2	136.2	116.4	61.20
1.80	840.0	624.0	398.4	291.0	232.6	199.2	180.0	139.7	120.0	63.60
1.75	936.0	668.4	416.4	302.6	236.4	204.0	183.6	142.0	122.4	64.80
1.70	1032	690.0	428.4	308.5	240.5	206.4	186.0	143.2	123.6	64.80
1.65	1064	733.2	442.8	316.8	244.0	208.8	188.4	144.3	124.8	66.00
1.60	1110	758.4	459.6	330.0	250.8	212.4	190.8	145.5	126.0	66.00

## Constant Power Discharge Characteristics : W(25°C)


F.V/ Time	30min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.90	1130	898.5	638.0	484.8	401.6	349.2	315.6	249.1	217.7	114.0
1.87	1243	975.7	676.6	507.7	423.3	366.0	333.6	259.6	227.0	118.8
1.83	1393	1064	720.0	534.3	443.8	380.4	344.4	268.9	235.1	123.6
1.80	1522	1135	744.1	546.3	452.3	388.8	352.8	274.7	240.9	126.0
1.75	1651	1185	768.2	563.2	458.3	398.4	358.8	278.2	244.4	128.4
1.70	1770	1198	787.5	572.9	465.5	402.0	362.4	280.5	246.8	129.6
1.65	1801	1251	809.2	584.9	471.5	405.6	366.0	282.9	247.9	129.6
1.60	1822	1289	828.5	604.2	483.6	409.2	368.4	284.0	249.1	130.8

All mentioned values are average values.


### Effect of temperature on long term float life




### Life characteristics of cyclic use



### Charge characteristic Curve for standby use



### Discharge characteristic Curve



### Long time discharge capacity for solar/wind application

Model	Capacity	C24 (Ah)	C48 (Ah)	C72 (Ah)	C100 (Ah)	C120 (Ah)	C240 (Ah)
		F.V=1.85VPC					
OPzV2-1200		1333	1500	1510	1530	1556	1582

### Capacity factors vs temperature (OPzV series)

Temperature	-30°C	-20°C	-10°C	0°C	10°C	20°C	25°C	30°C	40°C	45°C	50°C
Capacity	60%	75%	83%	89%	92%	99%	100%	103%	105%	107%	109%

### Discharge Current VS. Final Voltage

Discharge current	Final voltage (V)
$I_{dis} \leq 0.1110$	1.90
$0.1110 < I_{dis} \leq 110$	1.85
$110 < I_{dis} \leq 4110$	1.80
$4110 < I_{dis} \leq 6110$	1.75
$6110 < I_{dis} \leq 10110$	1.70
$I_{dis} > 15110$	1.60

Charge the batteries at least once every one year, if they are stored at 25°C.

Charging Method:

Constant Voltage	-0.2Cx2h+2.35~2.40V, 24h, Max. Current 0.2CA
Constant Current	-0.2Cx2h+0.1CAx 12h

### Maintenance & Cautions

#### Float Service:

- ※ Every month, recommend inspection every battery voltage.
- ※ Every three months, recommend equalization charge for one time.

#### Equalization charge method:

Discharge: 40~50% rate capacity discharge.

Charge: Max. current 0.2CA, constant voltage 2.35-2.40V/Cell charge 24h.

- ※ Effect of temperature on float charge voltage: -3mV/°C/Cell.

- ※ Service life will be directly affected by the number of discharge

cycles, depth of discharge, ambient temperature and charging method.