


Outer dimensions (mm)


TianChang sealed lead-acid rechargeable battery (VRLA battery) is leak-proof and maintenance free. The Superiority of VRLA battery is derived from its uniquely efficient oxygen recombination technology. The oxygen evolved from the positive plates diffuses through the micro porous glass fiber mat to the negative plates where it is changed back to water by recombination reaction, eliminating the need for water addition. The result is a maintenance free battery.

Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

Application


- Electric powered vehicles
- Golf cars and buggies
- PDA equipment as laptop computer,
- Camera, phone sets, medical sets
- Power tools, Lawn mowers, vacuum cleaners
- Electric Powered Toys
- Wheel Chairs

Specifications


Nominal Voltage		12V
Capacity (20 hr 25°C)		28Ah
Design Life		5 Years
Dimensions	Length	166 mm (6.54 inch)
	Width	175 mm (6.89 inch)
	Height	125 mm (4.92 inch)
	Total Height	125mm (4.92 inch)
Approx. Weight		8.60Kg
Capacity 25°C (77°F)	20 hr rate	28Ah
	10 hr rate	26.04Ah
	3 hr rate	23.80Ah
	1 hr rate	16.8Ah
Internal Resistance (Full charged Battery at 25°C (77°F))		10 mΩ

Capacity affected by Temperature (20hr)	40°C	102%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge at 25°C	3 month	Remaining capacity: 91%
	6 month	Remaining capacity: 82%
	12 month	Remaining capacity: 65%
Normal operating temperature		25°C ± 3°C (77°F ± 5°F)
Operating temperature range		-15°C ~ 50°C (5 ~ 122°F)
Float charging voltage (25°C)		13.6 to 13.8V
Cyclic charging voltage (25°C)		14.5 to 14.9V
Maximum charging current		11.20A
Terminal material		Copper
Maximum Discharge current		420A (5sec)


Charge characteristic Curve for standby use




Discharge characteristic (25°C/77°F)




Relationship between charging voltage and temperature




Self-discharge characteristic




Temperature effects on float life




Temperature effects on capacity



Life characteristics of Standby use



Cycle service life in relation to depth of discharge



Discharge Constant Current (Amperes at 77°F/25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	108.2	71.66	56.17	31.86	19.52	11.24	7.638	6.112	5.076	3.233	2.799	1.571
10.0V	104.3	69.87	54.37	31.45	18.98	11.01	7.497	6.028	4.990	3.220	2.770	1.514
10.2V	98.13	66.41	52.86	30.97	18.81	10.90	7.430	5.969	4.936	3.191	2.728	1.486
10.5V	88.21	62.10	49.86	30.12	18.44	10.75	7.364	5.911	4.877	3.163	2.714	1.442
10.8V	79.03	57.91	47.04	29.12	18.10	10.67	7.278	5.882	4.825	3.150	2.669	1.357
11.1V	69.15	53.09	43.40	28.02	17.62	10.24	7.136	5.830	4.776	3.125	2.627	1.335

Discharge Constant Power (Watts at 77°F/25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	1138	762.2	601.3	364.7	226.6	131.1	89.28	72.33	60.09	38.71	33.53	18.83
10.0V	1108	746.4	592.7	360.9	223.3	130.0	89.11	72.16	59.79	38.56	33.22	18.16
10.2V	1054	716.8	584.9	357.8	221.6	129.2	88.77	71.56	59.20	38.27	32.90	17.82
10.5V	962.1	687.3	554.4	350.5	218.6	128.2	88.41	70.91	58.50	37.95	32.56	17.32
10.8V	868.0	642.9	523.8	342.2	215.1	127.1	87.37	70.65	57.89	37.78	32.06	16.31
11.1V	765.5	598.6	493.3	332.8	211.1	122.7	85.67	69.94	57.34	37.52	31.59	16.05

(Note) The above characteristics data are average values.